



Technical data sheet

Threadlockers and Thread Sealants

Contents

1. Greenmark®	3
2. Comparison	4
2.1 Technical data	4
3. Threadlocker B222 Eco Low strength	5
3.1 Overview	6
3.2 Technical data	6
3.3 Application information	7
4. Threadlocker B243 Eco Medium strength	8
4.1 Overview	9
4.2 Technical data	9
4.3 Application information	10
5. Threadlocker B270 Eco High strength	11
5.1 Overview	12
5.2 Technical data	12
5.3 Application information	13
6. Thread sealant B577 Eco Medium strength	14
6.1 Overview	15
6.2 Technical data	15
6.3 Application information	16
7. Disclaimer	17

1. Greenmark®

The sub-brand Greenmark® comprises all marking systems of Lackfabrik Bäder GmbH & Co. KG, which are free of hazardous substances and have a particularly gentle effect on people and the environment.

It is the result of Bäder®'s strategic decision to rely largely on high-performance water-based marking systems for new developments and thus to decisively improve the ecological footprint. The Zero range marks the beginning and will be completed by further high-performance systems this year and in the coming year.

Properties of all Greenmark® products

- Water-based
- VOC-free
- HAP-free
- Non-hazardous goods
- Insulating
- Good media resistance



Designed for
the future

2. Comparison

2.1 Technical data

Uncured product	B222 Eco - low-strength	B243 Eco - medium-strength	B270 Eco - high-strength	B270 Eco - high-strength
Chemical base	Modified acrylate	Modified acrylate	Modified acrylate	Modified acrylate
Viscosity*	800 - 1500 mPas	1500 - 4000 mPas	300 - 900 mPas	20.000 - 40.000 mPas
Density**	1,08 - 1,10 g/ml	1,08 - 1,10 g/ml	1,09 - 1,13 g/ml	1,09 - 1,13 g/ml
Flash point***	> 65 °C	> 65 °C	> 65 °C	> 65 °C
Working temperature	10 - 40 °C	10 - 40 °C	10 - 40 °C	10 - 40 °C
Max. screw size	M36	M36	M20	M80
Hardened product				
Breakaway torque	5,5 - 11,5 Nm	15 - 25 Nm	>35 Nm	20 - 30 Nm
Temperature application range	-55 - 180 °C	-55 - 180 °C	-55 - 180 °C	-55 - 180 °C
Hardening properties				
Tangible after	approx 5 - 15 min	approx 5 - 15 min	approx 5 - 15 min	approx 5 - 15 min
Functional strength	approx 3 -6 h	approx 3 -6 h	approx 3 -6 h	approx 3 -6 h
Final strength	approx 12 - 24 h	approx 12 - 24 h	approx 12 - 24 h	approx 12 - 24 h

* At 25 °C, Brookfield viscometer.

** Measured according to DIN 53217, part 2 Density ball model 475/III

*** Measured according to DIN 51755

3. Threadlocker B222 Eco Low strength



3.1 Overview

The product cures (polymerises) in the absence of air-oxygen (anaerobic) and the catalytic action of the metal (metal contact). B222 Eco low-strength seals and closes many types of screw connections.

Properties

- Fast curing on a wide range of ferrous metals
- High resistance to vibration
- Secured screws easy to dismantle with tools
- High oil compatibility

Compared to conventional anaerobic adhesives, the Greenmark® products from Bäder® are completely label-free. In addition to a longer shelf life of 24 instead of 12 months, they also offer the user improved storage stability as well as increased temperature resistance of up to +180° C in use.

Available containers and maximum screw sizes

Container	Max. screw size
Bottle 10 ml	M36

Colours and item numbers

Colour	RAL	Item no.
 Purple, fluorescent	-	#73300

3.2 Technical data

Uncured product

Chemical base	Modified acrylate
Viscosity*	800 - 1500 mPas
Density**	1,08 - 1,10 g/ml
Flash point***	> 65 °C
Working temperature	10 - 40 °C

* At 25 °C, Brookfield viscometer.

** Measured according to DIN 53217, part 2 Density ball model 475/III

*** Measured according to DIN 51755

Hardened product

Breakaway torque	5,5 - 11,5 Nm
Temperature application range	-55 - 180 °C

Hardening properties

Tangible after	approx 5 - 15 min
Functional strength	approx 3 - 6 h
Final strength	approx 12 - 24 h

Storage and shelf life

The shelf life is 24 months at the optimum storage temperature of 5 °C to 23 °C in the sealed original container. A higher storage temperature leads to a significantly shorter shelf life. The storage temperature must not fall below 5 °C.

3.3 Application information

Low-strength threadlockers are not suitable for: Metal-plastic flange connections, in areas where gaseous oxygen is used and sealing against media with strongly oxidising acids.

The product is only to be used on standard metal threads. The affected surface must be free of grease and completely clean. Then use the threadlocker to completely fill the gap between the two parts, assemble the parts and seal them completely. Insufficient sealing can lead to leakage after a certain time. Do not move the parts once the curing process has started.

Allow the bonding to cure completely for 24 hours before putting into operation. In case of series production, lock or secure the bonding with a pipe wrench to avoid breaking the layer that is already in the curing process. Before using the product, please consult the safety data sheet.

4. Threadlocker B243 Eco Medium strength



4.1 Overview

The product cures (polymerises) in the absence of air-oxygen (anaerobic) and the catalytic action of the metal (metal contact). B243 Eco medium strength seals and closes many types of screw connections.

Properties

- DVGW approval (DIN EN 751-1 Class H)
- Fast curing on a wide range of ferrous metals
- High resistance to vibrations
- Secured screws moderately difficult to dismantle with tools
- Increased oil compatibility

Compared to conventional anaerobic adhesives, the Greenmark® products from Bäder® are completely label-free. In addition to a longer shelf life of 24 instead of 12 months, they also offer the user improved storage stability as well as increased temperature resistance of up to +180° C in use.

Available containers and maximum screw sizes

Container	Max. screw size
Bottle 10 ml	M36
Accordion bottle 50 ml	M36

Colours and item numbers

Colour	RAL	Item no.
● Blue, fluorescent	-	#12000

4.2 Technical data

Uncured product

Chemical base	Modified acrylate
Viscosity*	1500 - 4000 mPas
Density**	1,08 - 1,10 g/ml
Flash point***	> 65 °C
Working temperature	10 - 40 °C

* At 25 °C, Brookfield viscometer.

** Measured according to DIN 53217, part 2 Density ball model 475/III

*** Measured according to DIN 51755

Hardened product

Breakaway torque	15 - 25 Nm
Temperature application range	-55 - 180 °C

Hardening properties

Tangible after	approx 5 - 15 min
Functional strength	approx 3 - 6 h
Final strength	approx 12 - 24 h

Storage and shelf life

The shelf life is 24 months at the optimum storage temperature of 5 °C to 23 °C in the sealed original container. A higher storage temperature leads to a significantly shorter shelf life. The storage temperature must not fall below 5 °C.

4.3 Application information

Medium-strength threadlockers are not suitable for: Metal-plastic flange connections, in areas where gaseous oxygen is used and sealing against media with strongly oxidising acids.

The product is only to be used on standard metal threads. The affected surface must be free of grease and completely clean. Then use the threadlocker to completely fill the gap between the two parts, assemble the parts and seal them completely. Insufficient sealing can lead to leakage after a certain time. Do not move the parts once the curing process has started.

Allow the bonding to cure completely for 24 hours before putting into operation. In case of series production, lock or secure the bonding with a pipe wrench to avoid breaking the layer that is already in the curing process. Before using the product, please consult the safety data sheet.

5. Threadlocker B270 Eco High strength



5.1 Overview

The product cures (polymerises) in the absence of air-oxygen (anaerobic) and the catalytic action of the metal (metal contact). B270 Eco high-strength seals and closes many types of screw connections.

Properties

- Fastening of bolts in as-delivered condition, even with minor contamination
- Fastening of stud bolts as well as ball and roller bearings, which no longer need to be loosened
- Particularly suitable for heavily stressed screw connections

Compared to conventional anaerobic adhesives, the Greenmark® products from Bäder® are completely label-free. In addition to a longer shelf life of 24 instead of 12 months, they also offer the user improved storage stability as well as increased temperature resistance of up to +180° C in use.

Available containers and maximum screw sizes

Container	Max. screw size
Bottle 10 ml	M20
Accordion bottle 50 ml	M20

Colours and item numbers

Colour	RAL	Item no.
 Green, fluorescent	-	#75000

5.2 Technical data

Uncured product

Chemical base	Modified acrylate
Viscosity*	300 - 900 mPas
Density**	1,09 - 1,13 g/ml
Flash point***	> 65 °C
Working temperature	10 - 40 °C

* At 25 °C, Brookfield viscometer.

** Measured according to DIN 53217, part 2 Density ball model 475/III

*** Measured according to DIN 51755

Hardened product

Breakaway torque	>35 Nm
Temperature application range	-55 - 180 °C

Hardening properties

Tangible after	approx 5 - 15 min
Functional strength	approx 3 -6 h
Final strength	approx 12 - 24 h

Storage and shelf life

The shelf life is 24 months at the optimum storage temperature of 5 °C to 23 °C in the sealed original container. A higher storage temperature leads to a significantly shorter shelf life. The storage temperature must not fall below 5 °C.

5.3 Application information

High-strength threadlockers are not suitable for: Metal-plastic flange connections, in areas where gaseous oxygen is used and sealing against media with strongly oxidising acids.

The product is only to be used on standard metal threads. The affected surface must be free of grease and completely clean. Then use the threadlocker to completely fill the gap between the two parts, assemble the parts and seal them completely. Insufficient sealing can lead to leakage after a certain time. Do not move the parts once the curing process has started.

Allow the bonding to cure completely for 24 hours before putting into operation. In case of series production, lock or secure the bonding with a pipe wrench to avoid breaking the layer that is already in the curing process. Before using the product, please consult the safety data sheet.

6. Thread sealant B577 Eco Medium strength



6.1 Overview

Product curing (polymerisation) takes place in the absence of atmospheric oxygen (anaerobic) and the catalytic effect of the metal (metal contact). B577 Eco medium-strength seals and closes many types of threaded seals and screw connections.

Properties

- Seals conical/cylindrical pipe thread connections up to M80 (R3"), e.g. sprinkler systems and gas pipe systems
- Screw connections can be loosened with a tool
- Resistant to vibrations and other loads

Compared to conventional anaerobic adhesives, Greenmark® products from Bäder® are completely label-free. In addition to a longer shelf life of 24 instead of 12 months, they also offer the user improved storage stability and increased temperature resistance of up to +180° C in use.

Container, article number and max. screw sizes

Container	Item no.	Max. screw sizes
Bottle 10 ml	#72000-TF.01	M80
Accordion bottle 50 ml	#72000-TF.05	M80

Colour

Farbname	RAL
● Yellow, fluorescent	-

6.2 Technical data

Uncured product

Chemical base	Modified acrylate
Viscosity*	20.000 - 40.000 mPas
Density**	1,09 - 1,13 g/ml
Flash point***	> 65 °C
Working temperature	10 - 40 °C

* At 25 °C, Brookfield viscometer.

** Measured according to DIN 53217, part 2 Density ball model 475/III

*** Measured according to DIN 51755

Hardened product

Breakaway torque	20 - 30 Nm
Temperature application range	-55 - 180 °C

Hardening properties

Tangible after	ca. 5 - 15 min
Functional strength	ca. 3 -6 h
Final strength	ca. 12 - 24 h

Storage and shelf life

The shelf life is 24 months at the optimum storage temperature of 5 °C to 23 °C in the sealed original container. A higher storage temperature leads to a significantly shorter shelf life. The storage temperature must not fall below 5 °C.

6.3 Application information

The thread sealant B577 Eco medium-strength is not suitable for: Metal-plastic flange connections, in areas where gaseous oxygen is used and for sealing against media with strongly oxidising acids.

The product is only to be used on standard metal threads. The affected surface must be free of grease and completely clean. Then completely fill the gap between the two parts with the threadlocker, assemble the parts and seal them completely. Insufficient sealing can lead to leakage after a certain time. Do not move once the curing process has started.

Allow the bonding to cure completely for 24 hours before commissioning. In the case of series production, use pipe tongs to lock or secure the bond to prevent the layer already in the curing process from breaking open. Please consult the safety data sheet before using the product.

7. Disclaimer

The above information in this technical data sheet (TDS), in particular suggestions for the processing and range of application of our products, is based on our current knowledge and experience. Due to the different application possibilities and the application and working conditions beyond our control, we do not assume any liability for the suitability of our products for the relevant production processes under the specific working conditions as well as the intended processing purposes and results. In order to ensure such suitability, we recommend in any case sufficient prior self-trials and tests.

Any liability resulting from the instructions in this technical data sheet and any other written or verbal advice for the present product is expressly excluded, unless otherwise agreed in an individual contract, in the event of injury to life, limb or health, in the event of intent or gross negligence on our part or in the event of liability under mandatory product liability law.

The data contained herein is for information only and is believed to be reliable to the best of our knowledge. However, we cannot accept liability for results obtained by others over whose methods we have no control. It is the responsibility of the user to determine the suitability of any production methods mentioned herein for his purposes and to take such precautions as may be advisable to protect property and persons from the hazards which may be involved in the handling and use of these products. Accordingly, Lackfabrik Bäder GmbH & Co. KG specifically disclaims any warranty, express or implied, arising out of the sale or use of products manufactured by Lackfabrik Bäder GmbH & Co. KG products, including all warranties or guarantees of fitness for a particular purpose. Lackfabrik Bäder GmbH & Co. KG specifically disclaims any liability for consequential or indirect damages of any kind, including lost profits.